

# (12) UK Patent Application (19) GB (11) 2 139 206 A

(43) Application published 7 Nov 1984

(21) Application No 8311060

(22) Date of filing 22 Apr 1983

(71) Applicant  
VEB Leuna-Werke "Walter Ulbricht" (DR Germany),  
DDR - 4220 Leuna 3, German Democratic Republic

(72) Inventors  
Dr Wilfried Fuchs,  
Dr Horst Richter,  
Dr Roland Kober,  
Vendelin Kaufmann,  
Christina Muller

(74) Agent and/or Address for Service  
J. B. King,  
Kings Patent Agency Limited, Wardrobe Court, 146a  
Queen Victoria Street, London EC4V 5AT

(51) INT CL<sup>3</sup>  
C23F 11/18

(52) Domestic classification  
C1C 253 254 315 324 463 B

(56) Documents cited  
None

(58) Field of search  
C1C

(54) Preventing corrosion

(57) A hydrazine solution with improved initial activity in relation to oxygen dissolved in water which has been activated by the addition of complexes of trivalent cobalt with inorganic ligands as complex-formers, contains 2-amino-4-nitrophenol and or 2-acetamino-4-nitrophenol as a coactivator.

GB 2 139 206 A

## SPECIFICATION

## Process for improving the initial activity of activated hydrazine

5 This invention relates to a process for improving the initial activity of hydrazine in relation to oxygen 5  
dissolved in water, the hydrazine being activated by the addition of complexes of trivalent cobalt with  
inorganic ligands as complex-formers.

Activated hydrazine is used as a means for the removal of oxygen from water, particularly from boiler feed  
water and from water employed for preservation of idle plant, in order to prevent corrosion of tanks,

10 pipes, heat exchangers and other parts. 10

For the removal of oxygen dissolved in water various processes are employed. Preference is given to the  
use of hydrazine, which even at low temperatures and with the addition of suitable activators, reacts with  
oxygen dissolved in water to form hydrogen. Cationic and anionic complexes of trivalent cobalt, with  
inorganic ligands as complex-formers, are proposed as particularly suitable activators (GB ref:39291). Even

15 if these activators are regarded as advantageous, they have a disadvantage in that hydrazine activated in this 15  
way does not immediately reach its full reaction speed in relation to oxygen dissolved in water. The  
drawback may be surmounted either by gasification with air or by the addition of trivalent phenols as  
coactivators (GB ref:39274). These measures can improve the initial activity provided a relatively high  
concentration of activator is maintained, amounting to 0.5 to 1 g per litre of commercial hydrazine solution.

20 For special applications, however, these activator concentrations, though satisfactorily effective in 20  
themselves, may prove excessive in relation to the oxygen decomposition.

This invention seeks to improve the initial activity of activated hydrazine in relation to oxygen dissolved in  
water and at the same time to reduce the activator concentration required when the activators employed  
consist of complexes of the trivalent cobalt with inorganic ligands as complex-formers. The object of the  
25 invention is to provide a suitable activator system which ensures that hydrazine solution with the said 25  
activators in moderate concentration would immediately reach a high reaction speed in relation to oxygen  
dissolved in water, this process not requiring gasification with air.

According to this invention there is provided a process for improving the initial activity in relation to  
oxygen dissolved in water of hydrazine which has been activated by the addition of complexes of trivalent  
30 cobalt with inorganic ligands as complex-formers, in which process the activated hydrazine solution 30  
contains 2-amino-4-nitrophenol and/or 2-acetamino-4-nitrophenol as a coactivator.

Despite the fact that aminophenols with at least two nitro groups in the molecules are already known as  
activators, although they have to be used in comparatively high concentrations (DE 2601466), it has been  
found that neither 2-amino-4-nitrophenol nor a pure acetyl compound is satisfactorily effective when used as  
35 an activator. 35

Surprisingly it has been found that aqueous hydrazine solutions when produced in a suitable manner and  
containing the activators in the form of cationic or anionic complexes of trivalent cobalt with inorganic  
ligands as complex-formers and at the same time containing small quantities of 2-acetamino-4-nitrophenol  
or 2-amino-4-nitrophenol as coactivators, develop from the beginning of their action a fully adequate speed  
40 for the decomposition of oxygen dissolved in water. This enables the activator content to be reduced to 40  
below the value of 0.05 to 0.1% by mass in relation to the aqueous hydrazine solution, which is the usual  
proportion in this group of substances, with 220 g N<sub>2</sub>H<sub>4</sub>/l.

High reaction speeds in relation to oxygen are obtained with hydrazine solutions containing, 0.05 to 0.5g/l  
of cobalt complex as an activator and 0.05 to 0.25 g/l of 2-amino-4-nitrophenol or 2-acetamino-4-nitrophenol  
45 as a coactivator. With a view to maximum use of metal complex compound, hydrazine solutions containing 45  
0.05 to 0.5 g/l of sodium hexanitritocobaltate (III) and 0.05 to 0.25 g/l of 2-acetamino-4-nitrophenol mixed  
with 2-amino-4-nitrophenol are particularly suitable.

*Example*

50 1 ml of an aqueous hydrazine solution containing 220 g of hydrazine per litre, and with an activator 50  
consisting of 0.05 to 0.5 g/l of sodium hexanitritocobaltate (III) or cobalt (III)-hexamminochloride and a  
coactivator consisting of 0.05 to 0.25 g/l of 2-amino-4-nitrophenol or 2-acetamino-4-nitrophenol or a mixture  
of both compounds, is added to one litre of oxygenous water with about 6.5 mg O<sub>2</sub>/l, of which the pH value  
has been set to 10.4, the oxygen decomposition then being measured after 10 minutes. The temperature  
55 amounts to 293°K. The following table shows, after a reaction time of 10 minutes, the oxygen decomposition 55  
as a percentage in relation to the concentration of activator and of coactivator, compared with values  
obtained in the presence of only one substance in each case in addition to hydrazine.

	$\text{Na}_3\text{Co}(\text{NO}_2)_6$ (g/l)	$\text{Co}(\text{NH}_3)_6\text{Cl}_3$ (g/l)	2-Acetamino- 4-nitrophenol (g/l)	2-Amino- 4-nitrophenol (g/l)	$\text{O}_2$ -Decomposition after 10 minutes (%)	
5	—	—	1	—	13	5
	—	—	0.5	—	9	
	—	—	0.25	—	3	
10	—	—	—	2	12	10
	0.05	—	0.05	—	88	
15	0.1	—	0.1	—	96	15
	0.25	—	0.25	—	97	
	0.5	—	0.25	—	98	
20	—	—	—	—	—	20
	0.1	—	—	0.1	89	
25	0.25	—	—	0.25	100	25
	0.05	—	0.05	0.05	86	
	0.1	—	0.05	0.05	99	
30	—	0.25	—	0.25	100	30
	—	0.25	0.25	—	100	
35	—	0.1	0.05	0.05	89	35
	—	0.05	0.05	0.05	78	
	—	1.6	—	—	70	
40	1.5	—	—	—	62	40

## CLAIMS

- 45 1. Process for improving the initial activity, in relation to oxygen dissolved in water, of hydrazine which has been activated by the addition of complexes of trivalent cobalt with inorganic ligands as complex-formers, in which process the activated hydrazine solution contains 2-amino-4-nitrophenol and/or 2-acetamino-4-nitrophenol as a coactivator. 45
- 50 2. Process in accordance with Claim 1, wherein the hydrazine solution contains 0.05 to 0.5 g/l cobalt complex as an activator and a mixture of 0.05 to 0.25 g/l 2-amino-4-nitrophenol and 2-acetamino-4-nitrophenol as a coactivator. 50
3. Process for improving the initial activity of hydrazine in relation to oxygen dissolved in water as described herein and exemplified.